

PARTIAL AND COMPLETE REPLACEMENT OF FINE AGGREGATE FROM STONE DUST

Surendra Pratap¹, Kundan Kulbhushan²

¹M.Tech, ²Assistant Professor
Department of civil engineering,
Maharishi University of Information Technology, Lucknow, U.P.

Abstract: In present days natural sand of good quality are becoming scarcer and costlier due to non-accessibility of river during entire year, illegal dredging, rapid growth of construction activities etc. So it is necessary to search an alternative material to use as natural sand in construction activities. Stone dust is such an alternative material which can be effectively being used in construction as partial replacement of natural sand. Hence present study taken a view to verify the suitability and potential use of stone dust in concrete mix as fine aggregate. To accomplish this an experimental program was planned for cast specimen cubes at an interval of 10 percent replacement of fine aggregate with stone dust in concrete. Results shows natural sand can be effectively replace with stone dust and maximum strength attains at 60 percent replacement of natural sand with stone dust based on compressive strength.

Index Terms: Concrete, coarse aggregate, cement, stone dust, compressive strength test.

I. INTRODUCTION

Concrete is the most widely used building material in the world, as well as the largest user of natural resources with annual consumption of 12.6 billion tons [Mehta, 2002]. Fundamentally comprised of coarse and fine aggregates, cement and water, concrete in some cases also contains additional chemical or mineral admixtures for specific purposes. Most of the ingredients, produced from virgin resources, are non-renewable, or strictly speaking non-sustainable. Recently, there has been an increasing awareness of environmental protection, resource and energy conservation, and sustainable development globally. Many research works have been initiated and developed to make concrete more sustainable, mainly in reducing its negative impacts on environment and reserve natural raw materials. Higher degree of sustainability of concrete can be achieved by replacing its virgin ingredients, including cement and aggregates, by other materials, such as reclaimed materials from old structures, by-products from industrial process and recycled solid wastes. Apart from saving raw materials and protecting environment, additional benefits are usually accompanied with the production of sustainable concrete, such as reduced landfills and dumping volumes, decreased amount of energy and CO₂ emission, as well as enhanced life cycle performance and lowered cost in maintenance during the whole life of structures. Quantities of studies have proved the successful substitution of cement in concrete by some pozzolanic by-product materials, like pulverized fly ash and ground granulated blast-furnace slag (GGBS) [Malhotra, 1999; Mehta, 2001]. Besides the reduction in cement content and cost, workability, long term mechanical properties and durability can also be improved for such concrete, resulting in higher sustainability. Also, recycled coarse aggregates and manufactured coarse aggregates have been widely accepted in construction as alternative virgin coarse aggregates. However, the research and development of fine aggregate (sand) substitution is relatively slow.

The definition of fine aggregate is the aggregate passing the 9.5-mm sieve and almost entirely passing the 4.75-mm sieve and predominantly retained on the 75- μ m sieve, either in a natural condition or after processing. Sand refers to fine aggregate resulting from natural disintegration and abrasion of rock or processing of completely friable sandstone, while manufactured sand means fine aggregate produced by crushing rock, gravel, iron blast furnace slag, or hydraulic concrete.

Sand consumes around 20~27% of concrete by volume, thus playing an important role in fresh and hardened properties of concrete [Neville, 1995]. The reserve of natural sand is depleting and the conventional sand mining, quarrying and river and ocean dredging is being criticized for their negative influences on environment, such as drinking water degradation, land and coast corrosion, flood and species depletion. Therefore, the necessity to seek sound replacements of natural sand for concrete is compelling to satisfy the sustainable development in concrete.

II. MATERIALS AND METHODS

MATERIALS

Cement - Portland Pozzolana Cement (fly ash based) brand name Birla Gold confirming to IS 1489 (Part 1) - 1991 was used in this study.

Fine Aggregate - River sand available in Allahabad confirming to IS 383-1970, zone II used in the study. It was completely passed by 4.75 mm IS sieve. Fineness modulus and specific gravity was 2.76 and 2.3 respectively.

Coarse Aggregate - Locally available coarse aggregate having two fraction 20mm and 10mm sizes individually sieved was used in the present study. One fraction completely passed through 20 mm sieve and another 10 mm sieve. For mix the ratio of these aggregates was 60:40 respectively.

Stone dust - Grey color stone dust was purchased from local stone crushing units. It was initially dry in condition and thoroughly retained on IS 150 μ sieve before preparation of mix. Fineness modulus and specific gravity was 2.85 and 2.4 respectively.

METHODS

Stone dust, Aggregate and Cement were purchased from hardware shop form market and they are bring directly to concrete technology laboratory. About 20 kg of stone dust were bought and 20 kg of course as well as fine aggregate and 1 sac (50 kg) of cement was purchased. The demand of such building material is high in the market that is why they are easily available at any of the hardware shop. The stone dust will be mix in the fine aggregate in the ratio of 50% and 100% by weight. As the study is about partial replacement and complete replacement so for partial replacement mixing of stone dust with fine aggregate was necessary. After the mixing of stone dust with fine aggregate then preparation of concrete was started and the M20 grade ratio was followed for making concrete. The prepared concrete is now subjected to the casting of cube. About 20 cubes will be casted and then it will be immerse in the curing tank for 3, 7, 14, 21 & 28 days. Compressive strength test will be performed on the casted and cured cube on the specified days. On the casted cube this is the only test which will provide the strength gain by the cube at specified days.

III. RESULTS

The sample preparation as well as analysis of the cured concrete cubes were done according to the IS 456:2000.

The results for compressive strength test are:-

Stone dust ratio	25 %	50%	100%
Testing days			
3 day	6.99 N/mm ²	7.24 N/mm ²	7.95 N/mm ²
7 day	11.23 N/mm ²	12.36 N/mm ²	12.88 N/mm ²
14 day	17.53 N/mm ²	17.07 N/mm ²	18.00 N/mm ²
21 day	18.00 N/mm ²	18.43 N/mm ²	18.93 N/mm ²
28 day	19.05 N/mm ²	19.50 N/mm ²	19.95 N/mm ²

IV. CONCLUSION

In the experimental study stone dust, the cubes were tested for 3 days, 7days, 14days, 21 days and 28 days compressive strength 25%, 50% and 100% replacement of fine aggregate by stone dust in M20 grade concrete. The 3 days, 7days, 14days, 21 days and 28 days compressive strength is shown in tables respectively. The result of cube that were tested for 28 days is shown tables. It has been observed that the results obtained in all compressive strength are comparable with that of concrete with stone dust.

The test results shows that the sample having 25% stone dust content showed its maximum strength on 14 day test with 17.53 N/mm². The test result of sample of sample 2 having 50% stone dust content showed its maximum strength on 21 as well as 28 day test with 18.43 and 19.50 N/mm². The test result of sample of sample 3 having 100% Stone dust content showed its maximum strength on 14, 21 and 28 day test with 18.00, 18.93 and 19.95 N/mm².

The compressive strength test results shows that the sample containing 50% and 100% stone dust content show good compressive strength on 28 days but on comparing test results of both the sample, sample containing 100% Stone dust is showing better result than other one.

The following conclusions were drawn from the present experimental study.

1. The compressive strength of concrete for grade M20 with stone dust as fine aggregate were found to be comparable with the concrete.
2. With the increase in stone dust content in the concrete there is a gain in strength upto 98%
3. Stone dust can effectively be used in plain cement concrete in place of fine aggregate.
4. The Physical and chemical properties of stone dust is satisfied by the requirements of code provision in properties studies Natural river sand, if it is replaced by hundred percent Quarry Stone Dust from quarries, may sometimes give equal or better than the reference concrete made with Natural Sand, and in the terms of flexural and compressive strength studies.
5. From this test, replacement of OPC cement with this stone waste material provides maximum compressive strength at 100% replacement.
6. Non- availability of sand at reasonable costs as fine aggregate in cement concrete for various reasons, search for alternative material stone crusher dust qualifies itself as a suitable substitute for sand at very low cost.

REFERENCES

- [1] Ahmed AAM, Yusuf MA (2009). "Using of stone powder as an alternative of sand" B. Sc. Eng. Thesis, Civil and Environmental Engineering Department, Shahjalal University of Science and Technology, Sylhet, Bangladesh.
- [2] Ahmed M (1996). Appropriateness of Stone Shingles in Cement Concrete. ICI Bull. No. 54 Jan. - Mar. Indian Concrete Institute, India.
- [3] Aziz MA (1995). Engineering Materials. Z and Z Computer and Printers, Dhaka, Bangladesh.
- [4] Chamberlain B (1995). Concrete, A material for the new Stone Age, a mast module, Material Science Technology.
- [5] Economic and Social Commission for Asia and the Pacific (ESCAP) (2001). Opportunity and Challenges for Tourism Investment, found at http://www.unescap.org/ttdw/Publications/TPTS_pubs/Toreview_No21_2172.pdf.
- [6] Ferguson PM, Breen JE, Jiras JO (1988). Reinforced Concrete Fundamentals, 5th Ed., John Wiley & Sons, p. 1.
- [7] Isabelle MC, Dolors V, John DR, Ignacio D, Anabel P (1999). Potential impacts of gravel extraction on Spanish populations of river blennies *Salaria fluviatilis* (Pisces, Blenniidae), Biol. Conserv., 87(3): 359-367, March, doi: 10.1016/S0006-3207(98)00072-X.
- [8] Islam MA, Sayem A, Iqbal M, Shahariar MH, Imtiaz S (2010). Prospects for the stone crusher industry in Jaflong region of Sylhet, Proceedings of the conference on Engineering Research, Innovation and Education CERIE, 11- 13 Jan., Sylhet, Bangladesh.
- [9] Kabir MI (2006). "A Study conducted for Medium Grade Cement Concrete Keeping all other parameters same Accept aggregate type, W/C, and mix design ratio" B.Sc Engineering Thesis, Civil and Environmental Engineering Department, Shahjalal University of Science and Technology, Sylhet, Bangladesh.
- [10] Kameswari KSB, Bhole AG, Paramasivam R (2001). Evaluation of Solidification (S/S) Process for the Disposal of Arsenic Bearing Sludge in Landfill sites. Environ. Eng. Sci., 18: 167-176.
- [11] Kishore K (1995). High Strength Concrete. ICI Bull. No. 51 April-June. Indian Concrete Institute, India.
- [12] Mahzuz HMA, Alam R, Alam MN, Basak R, Islam MS (2009). Use of arsenic contaminated sludge in making ornamental bricks". Int. J. Environ. Sci. Technol., Spring, ISSN: 1735-1472, 6(2): 291-298.
- [13] Mahzuz HMA, Tajmunnahar HBM (2010). "Assessment of present environmental situation and strategy formulation for future extraction of natural resources of Jaflong" Proceedings of the conference on Engineering Research, Innovation and Education CERIE, 11-13 January, Sylhet, Bangladesh.
- [14] Mobasher B (1999). Aggregates: Fineness Modulus. Available from: <http://www4.eas.asu.edu/concrete/aggregates/sld013.htm>.
- [15] Sanchez F, Garrabrants AC, Vandecasteele C, Moszkowicz P, Kosson DS (2002). Environmental Assessment of Waste Matrices Contaminated with Arsenic. J. Hazard. Mater. 96: 229-257.
- [16] IS:383-1970, Specification for Coarse and fine aggregate from natural sources for concrete, Bureau of Indian standard, New Delhi.
- [17] IS:2386(Part I to V)-1963, Methods of Test for Aggregates for Concrete, Bureau of Indian standard, New Delhi.
- [18] IS:1489(Part I)-1991, Specification for Portland pozzolana cement (Fly ash based), Bureau of Indian standard, New Delhi.
- [19] IS:1199-1991, Methods for sampling and analysis of concrete, Bureau of Indian standard, New Delhi.
- [20] IS:9103-1999, Concrete Admixtures - specification, Bureau of Indian standard, New Delhi.
- [21] IS:10262-2009, Guidelines for concrete mix design proportioning, Bureau of Indian standard, New Delhi.
- [22] IS:516-1959, Methods of Tests for Strength of Concrete, Bureau of Indian standard, New Delhi.
- [23] Franklin eric kujur, Vikas Srivastava, V.C. Agarwal, Denis and Ahsan Ali (2014) "Stone dust as partial replacement of fine aggregate in concrete", Journal of academia and industrial research, volume 3, issue 3, pp 148-151.
- [24] M.S. Shetty (2013) "Concrete Technology Theory and Practice", S. Chand & company Pvt.Ltd, New Delhi.
- [25] Lakhn nagpal, arvind dewangan, Sandeep dhiman, Sumit kumar (2013) "Evaluation of strength characteristics of concrete using crushed stone dust as fine aggregate", IJITEE, volume 2, issue 6, pp 102-104.
- [26] G. Balamurugan, P.Perumal (2013) "Use of quarry dust to replace sand in concrete –An experimental study", IJSRP, volume 3, issue 12, pp 1-4.
- [27] A.D. Pofale, Syed Raziuddin Quadri (2013) "Effective Utilization of crusher dust in concrete using Portland pozzolana cement", IJSRP, Volume 3, Issue 8, pp 1-10.