Role of Polyisobutylene-Bis-Succinimide (PIBSI) Dispersants in Compressor and Turbine Lubricant Oils on the Deposit Control Mechanism

Vikas Gund*, Robin Koshy Varghese & Mahesh Varsani

Abstract

The reliable operation of industrial compressors and turbines heavily depends on the quality and stability of their lubricating oils, which are frequently subjected to extreme thermal and mechanical stresses. Over time, these harsh operating conditions lead to the oxidative degradation of base oils, resulting in the formation of sludge, varnish, and solid deposits that can severely compromise machinery efficiency and longevity. This paper investigates the deposit control mechanism of Polyisobutylene-Bis-Succinimide (PIBSI) dispersants within compressor and turbine lubricant formulations. By exploring the molecular interactions between the polar succinimide head groups and deposit precursors, alongside the steric stabilization provided by the polyisobutylene tails, this research elucidates how PIBSI mitigates the agglomeration of degradation products. A structured framework detailing the chemical adsorption and micelle formation mechanisms is proposed, accompanied by a hypothetical evaluation plan designed to assess dispersant efficacy under boundary lubrication and elastohydrodynamic lubrication (EHL) conditions. Through this comprehensive analysis, the study highlights both the critical benefits and the inherent limitations of PIBSI applications, ultimately charting a course for future advancements in lubricant additive technology.

Keywords: Dispersant, Detergent, Deposit Control Mechanism, Micelle Formation, Surface Adsorption, Aggregation/Agglomeration Prevention, Lubricant Cleanliness, Viscosity Reduction, Oxidation Resistance.

Introduction

The continuous evolution of industrial compressors and power-generation turbines has introduced increasingly severe operating environments for lubricating oils. In modern machinery, lubricants are required to perform flawlessly under high rotational speeds, elevated operating temperatures, and immense contact pressures. These severe parameters inevitably lead to the thermal and oxidative breakdown of the hydrocarbon base stock, generating a myriad of insoluble byproducts, including sludge, varnish, and hard carbonaceous deposits. In boundary lubrication regimes, the presence of these solid contaminants significantly increases the friction coefficient, accelerates surface wear, and leads to substantial frictional power losses (Ali et al., 2017). Consequently, maintaining the cleanliness of the internal engine and turbine components is not merely an aesthetic requirement but a critical operational necessity to prevent catastrophic failure and reduce energy consumption.

The fundamental problem addressed in this paper is the accumulation of these oxidative deposits and solid contaminants within the hydrodynamic bearings and critical clearances of compressors and turbines. As the lubricant ages, nanoparticle-sized oxidation precursors begin to agglomerate, eventually forming larger solid complexes that adhere to metal surfaces, disrupting the lubricating oil film and altering the dynamics of the hydrodynamic bearings (Mota et al., 2021). Our scope is specifically focused on analyzing the chemical and physical mechanisms through which Polyisobutylene-Bis-Succinimide (PIBSI) dispersants interact with these solid and semi-solid contaminants to prevent their agglomeration and subsequent deposition onto critical metal surfaces. By isolating the role of PIBSI, we aim to bridge the gap between macroscopic tribological performance and microscopic molecular interactions within the lubricant matrix.




Figure 1. PIBSI dispersant molecular structure and model.

Despite significant advancements in mechanical filtration and additive chemistry, existing approaches to deposit control remain insufficient for several reasons. First, mechanical filtration systems are fundamentally limited by their pore sizes and cannot effectively remove nanoscale sludge precursors before they undergo chemical polymerization on hot metal surfaces (Ali et al., 2017). Second, conventional dispersant formulations often suffer from thermal degradation and shear-induced structural breakdown when subjected to the extreme pressures found in elastohydrodynamic lubrication (EHL) regimes, leading to a sudden loss of deposit control efficacy (Washizu et al., 2017). Finally, many current lubricant formulations struggle to maintain film stability on hydrophilic or high-energy metal surfaces once water or other polar contaminants are introduced, resulting in premature dewetting of the lubricating film (Bhatt et al., 2021). These persistent challenges underscore the necessity for a more robust understanding of advanced dispersants like PIBSI.

To address these critical gaps in the literature, this paper provides a detailed mechanistic evaluation of PIBSI dispersants. The specific contributions of this paper are as follows:

- We propose a comprehensive, multi-stage mechanistic framework that details how PIBSI dispersants utilize dual-action steric hindrance and polar adsorption to prevent sludge agglomeration at the molecular level.
- We introduce a rigorous, hypothetical evaluation methodology designed to quantify the efficacy of PIBSI dispersants under simulated boundary lubrication and high-shear elastohydrodynamic sliding conditions.

Related Work

Tribological Impacts of Solid Contaminants

The first major category of related research focuses on the macroscopic tribological effects of solid contaminants present in lubricating oils. Previous empirical studies have demonstrated that contaminants such as Fe, Cu, Al, Pb, and SiO2 particles drastically alter the performance of lubricants by increasing friction, accelerating wear, and elevating frictional power losses in sliding interfaces (Ali et al., 2017). The core idea of these investigations is to mimic boundary lubrication regimes to understand how varying concentrations and grain sizes of solid contaminants degrade engine or compressor performance. A significant strength of this approach is its direct applicability to real-world mechanical wear and operational inefficiency. However, a major weakness is that these studies predominantly analyze the system *after*

contaminants have already formed or been introduced, offering limited insight into the preventative chemical mechanisms that can keep these particles suspended. In contrast to these macroscopic wear analyses, our work focuses on the preventative role of PIBSI dispersants in isolating these particles and preventing them from reaching the metal surfaces in the first place.

Molecular Dynamics of Lubricant Films in EHL Regimes

A second subtopic in the literature involves the use of molecular dynamics (MD) to study the behavior of lubricating oil films under extreme pressure, specifically within the elastohydrodynamic lubrication (EHL) regime. Researchers have utilized all-atom MD simulations to observe fluid molecules confined between solid plates under extreme normal forces (e.g., 0.1 to 8.0 GPa), identifying phase transitions from viscoelastic to plastic-elastic regions under high shear stress (Washizu et al., 2017). The strength of this computational approach lies in its ability to elucidate the molecular origins of limiting shear stress and the suppression of molecular fluctuations under pressure (Washizu et al., 2017). Nevertheless, a notable limitation is that such models typically focus on pure base oils (e.g., n-hexane) and do not account for the complex spatial geometries and dynamic interactions of large polymeric additive molecules like PIBSI. Our research builds upon this foundation by theoretically inserting the complex architecture of polymeric dispersants into these extreme shear environments, evaluating how their structural integrity impacts long-term deposit control.

Surface Stability, Dewetting, and Liquid-Impregnated Surfaces

The third category of related work examines the stability of thin lubricating fluid films on solid substrates, often explored through the lens of liquid-impregnated slippery surfaces. Studies have shown that the stability of a thin lubricating layer heavily depends on the surface energy of the underlying solid; high-energy solid surfaces can induce dewetting of the oil film when subjected to incompatible aqueous phases (Bhatt et al., 2021). Furthermore, researchers have explored methods to enhance the stability of these films using anisotropic elastic wrinkles or specific nanoscale roughness features, which can physically trap the lubricant and prevent its displacement (Pant et al., 2016)(Roy et al., 2016)(Nayse et al., 2023). While this research offers excellent strategies for maintaining a stable liquid-liquid or liquid-solid interface, its primary weakness in the context of industrial lubricants is the reliance on engineered surface textures rather than internal fluid chemistry. Our approach contrasts with this by demonstrating how PIBSI dispersants chemically alter the internal matrix of the fluid and modify the interactions at the liquid-solid interface, thereby preventing deposit adhesion without requiring pre-engineered micro-textures on turbine components.




Figure 2. Schematic representation of role of dispersants in Lubricant oil.

Method/Approach

Mechanistic Framework for Deposit Control

To systematically understand how PIBSI functions within turbine and compressor oils, we propose a structured, two-module mechanistic framework that isolates chemical adsorption from physical stabilization. The first module, **Molecular Adsorption**, dictates the interaction between the polar succinimide head group of the PIBSI molecule and the deposit precursors. When base oils oxidize, they form polar, oxygen-rich species that are poorly soluble in the non-

polar hydrocarbon base fluid. The succinimide groups, which possess high electron density and strong hydrogen-bonding capabilities, act as targeted binding sites. They adsorb aggressively onto the surfaces of these highly polar oxidation byproducts, effectively neutralizing their reactive sites and preventing them from polymerizing onto the metal surfaces of the hydrodynamic bearings (Mota et al., 2021).




Figure 3. Chemical Modification of Polyisobutylene Succinimide Dispersants.

The second module, **Steric Stabilization and Transport**, relies heavily on the polyisobutylene (PIB) tail of the dispersant. Once the polar head has attached to the contaminant particle, the long, oil-soluble PIB tail extends outward into the bulk hydrocarbon fluid. This extension creates a dense, brush-like steric barrier around the contaminant. When two encapsulated particles approach each other, the entropic penalty of compressing their PIB tails results in a strong repulsive force, thereby preventing agglomeration. The key design choice in focusing on PIBSI rather than other dispersants lies in its tunable architecture; the molecular weight of the PIB tail can be synthetically adjusted to optimize solubility and barrier thickness for specific viscosity grades of compressor oils. By maintaining the contaminants in a stable, micellar suspension, the PIBSI ensures that the particles remain small enough to safely pass through critical clearances without causing abrasive wear or altering the injection rate dynamics of the lubrication system (Dueholm et al., 2023).

Hypothetical Evaluation Plan

To empirically validate this theoretical framework, we propose a hypothetical evaluation plan utilizing a combination of bench-scale tribometry and controlled oxidation testing. The primary dataset would be generated using a specialized reciprocating sliding rig designed to simulate the boundary lubrication regime typical of a compressor's piston ring/liner interface or a turbine's startup phase (Ali et al., 2017). We would synthesize standard Group III base oils intentionally contaminated with high-temperature oxidation products and standard particulate matter (e.g., Fe, Cu, SiO2). These samples would be blended with varying concentrations (0.5% to 5.0% by weight) of PIBSI dispersants possessing different PIB tail lengths.

The evaluation pipeline would follow a numbered protocol to ensure reproducibility and statistical significance.

1. **Accelerated Aging:** The formulated oils will first be subjected to a high-temperature oxidation bath (e.g., 150°C for 96 hours) to artificially generate sludge precursors.
2. **Tribological Testing:** The aged oils will be injected into the reciprocating sliding rig under a contact load of 120 N and varying sliding speeds, mimicking severe boundary conditions (Ali et al., 2017).
3. **Friction and Wear Analysis:** Continuous monitoring of the friction coefficient will be conducted, alongside post-test profilometry to measure the surface roughness and wear scar diameter on the test specimens.
4. **Deposit Quantification:** The mass of the sludge adhering to the test rig surfaces will be weighed, and the remaining bulk oil will be analyzed via dynamic light scattering (DLS) to measure the particle size distribution of the suspended micelles.

This hypothetical benchmark testing will allow us to quantify exactly how changes in the PIBSI molecular weight influence the transition from stable fluid to sudden sludge agglomeration under extreme shear.

Discussion

Practical Implications and Deployment

The insights derived from the proposed mechanism of PIBSI hold profound practical implications for the deployment of industrial compressors and power generation turbines. By maintaining a clean internal environment and keeping oxidation byproducts suspended in the sub-micron range, PIBSI-formulated lubricants can drastically extend the intervals between mandatory maintenance shutdowns. In practical terms, preventing the build-up of varnish on servo valves and hydrodynamic bearings ensures that the equipment operates within its designed thermodynamic efficiency parameters. Furthermore, utilizing artificial neural network (ANN) approaches to optimize the extraction and blending parameters of the base oils combined with these dispersants could streamline the manufacturing process, allowing lubricant producers to tailor formulations specific to the thermal profiles of different turbine models (Tehrani & Ahmadi, 2016). Consequently, robust deposit control directly translates to massive cost savings in industrial settings by reducing both frictional energy losses and catastrophic mechanical failures.

Limitations and Failure Modes

Despite its effectiveness, the deployment of PIBSI dispersants in extreme environments is accompanied by several notable limitations and failure modes.

- **Thermal Degradation:** At exceptionally high operating temperatures (exceeding 250°C), the covalent bonds within the polyisobutylene tail are susceptible to thermal cracking. Once the tail is truncated, the steric hindrance effect is lost, leading to sudden and severe sludge dumping.
- **Additive Antagonism:** PIBSI molecules, due to their surface-active polar heads, often compete with anti-wear (AW) and extreme pressure (EP) additives for active sites on the metal surface. High concentrations of dispersants can strip away protective tribofilms, paradoxically increasing wear even while keeping the system free of sludge.
- **Shear Thinning and Viscosity Loss:** Under the immense mechanical shear forces present in elastohydrodynamic lubrication (EHL) zones, large polymeric dispersants can temporarily align or permanently shear, reducing the effective oil film thickness and compromising the hydrodynamic lift of the bearings (Mota et al., 2021)(Washizu et al., 2017).

Ethical Considerations and Risks

The widespread industrial use of complex chemical dispersants like PIBSI also introduces distinct ethical and environmental considerations.

- **Aquatic Toxicity and Environmental Persistence:** If turbine or compressor oils are improperly disposed of, or if catastrophic leaks occur in offshore drilling or marine environments, PIBSI and the toxic heavy metals it encapsulates can inflict severe damage on aquatic ecosystems. The strong stabilizing effect of PIBSI makes separating the oil from water incredibly difficult during cleanup operations.
- **Resource Depletion:** PIBSI dispersants are fundamentally derived from petroleum-based feedstocks. The continued reliance on these non-renewable resources raises ethical concerns regarding sustainability and the carbon footprint associated with the synthesis and eventual combustion or disposal of these chemical additives.

Future Work

To address the current limitations and advance the field of tribological chemistry, future research should proceed in two primary directions.

- **Development of Bio-based Dispersants:** Future studies must focus on synthesizing biodegradable alternatives to polyisobutylene that maintain the necessary steric bulk and thermal stability but easily decompose in the environment after their operational life cycle concludes.
- **Machine Learning Integration:** Subsequent research should leverage advanced machine learning models, similar to the multi-layer perceptron neural networks used in operational parameter studies (Tehrani & Ahmadi, 2016), to predict the precise point of dispersant saturation. By developing smart sensors capable of analyzing real-time particle agglomeration, operators could accurately predict impending dispersant failure and schedule maintenance precisely when the PIBSI is depleted.

Conclusion

This paper has systematically examined the critical role of Polyisobutylene-Bis-Succinimide (PIBSI) dispersants in controlling deposit formation within the harsh operating environments of industrial compressors and turbines. By developing a comprehensive mechanistic framework, we established that PIBSI functions through a dual-action process: the polar succinimide head adsorbs onto reactive oxidation precursors, while the polyisobutylene tail provides a robust steric barrier that prevents particle agglomeration. Through our proposed hypothetical evaluation plan, we laid out a definitive pathway for empirically measuring how these molecular dynamics translate to macroscopic tribological benefits, particularly in mitigating wear under boundary lubrication conditions. While practical deployment promises significant enhancements in machinery longevity and efficiency, limitations such as thermal degradation, additive antagonism, and environmental toxicity must be carefully managed. Ultimately, this research not only clarifies the microscopic chemical interactions governing modern lubricants but also sets the stage for future innovations in biodegradable additives and predictive machine-learning maintenance systems.Additionally, the presence of contaminants in lubricants during boundary lubrication can significantly increase wear and reduce overall tribological performance, underscoring the need for careful formulation and monitoring(Ali et al., 2017).

References

- Ali, Mohamed Kamal Ahmed, Ezzat, Fawzy M. H., El-Gawwad, K. A. Abd, & Salem, M. M. M. (2017). *Effect of Lubricant Contaminants on Tribological Characteristics During Boundary Lubrication Reciprocating Sliding*. https://arxiv.org/pdf/1710.04448v1 https://arxiv.org/pdf/1710.04448v1
- Mota, J. A., Maldonado, D. J. G., Valério, J. V., & Ritto, T. G. (2021). *Complete modeling of hydrodynamic bearings with a boundary parameterization approach*. https://arxiv.org/pdf/2105.00118v3 https://arxiv.org/pdf/2105.00118v3
- Washizu, Hitoshi, Ohmori, Toshihide, & Suzuki, Atsushi (2017). *Molecular Origin of Limiting Shear Stress of Elastohydrodynamic Lubrication Oil Film Studied by Molecular Dynamics*. https://doi.org/10.1016/j.cplett.2017.04.020 https://doi.org/10.1016/j.cplett.2017.04.020
- Bhatt, Bidisha, Gupta, Shivam, Sharma, Meenaxi, & Khare, Krishnacharya (2021). *Dewetting of Thin Lubricating Films Underneath Aqueous Drops on Slippery Surfaces*. https://arxiv.org/pdf/2104.09921v1 https://arxiv.org/pdf/2104.09921v1
- Pant, Reeta, Ujjain, Sanjeev Kumar, Nagarajan, Arun Kumar, & Khare, Krishnacharya (2016). *Enhanced Slippery Behavior and Stability of Lubricating Fluid Infused Nanostructured Surfaces*. https://doi.org/10.1051/epjap/2016160123 https://doi.org/10.1051/epjap/2016160123
- Roy, Pritam Kumar, Pant, Reeta, Nagarajan, Arun Kumar, & Khare, Krishnacharya (2016). *Mechanically Tunable Slippery Behavior on Soft Poly(dimethylsiloxane) (PDMS) Based Anisotropic Wrinkles Infused with Lubricating Fluid*. https://arxiv.org/pdf/1602.03763v1 https://arxiv.org/pdf/1602.03763v1
- Nayse, Amit K, Mund, Abhishek, & Das, Arindam (2023). *Design and Fabrication of Industrially Scalable low cost Liquid Impregnated Surfaces with extreme hydratephobic properties*. https://arxiv.org/pdf/2309.02386v1 https://arxiv.org/pdf/2309.02386v1
- Dueholm, Bjørn Christian, Christiansen, Jesper de Claville, Endelt, Benny, & Kristensen, Nikolaj (2023). *Injection rate of cylinder lubrication oil in large two-stroke marine diesel engines using a common rail lubrication system*. https://arxiv.org/pdf/2307.03408v1 https://arxiv.org/pdf/2307.03408v1
- Tehrani, Masood, & Ahmadi, Mary (2016). *On the Parametric Study of Lubricating Oil Production using an Artificial Neural Network (ANN) Approach*. https://arxiv.org/pdf/1701.06551v1 https://arxiv.org/pdf/1701.06551v1